


From Page No. ___



MW Weight
 d) 2860-5 0.1g
 (2) 4560-5500 0.175g

Procedure A VIAL (15 ml)
 Add (1)
 Add (2) + 5 ml THF
 stirred to get homogeneous solution
 Evaporate to dryness by blow N₂.
 place in the oven at 110°C for 1h
 Cooled to RT
 Washed by THF (2x10ml)
 Dry at 110°C for 0.5h
 yield ~0.23g 84% gelation.

To Page No. ___

Witnessed & Understood by me,

Lamine Upelmin

Date

11/3/98

Invented by

JIN HU

Recorded by

JIN HU

Date

10-5-98

EXHIBIT 1